

7071 Oakwood Drive
Niagara Falls, ON L2G 0J3
Tel: 905-356-1581
www.niaccoat.com

LIQUISTONE [®]

npc


Niagara Protective **Coatings**

— **SINCE 1957** —

@niagaraprotectivecoatings



 905-356-1581 |  <http://niacoat.com/> |  info@niacoat.com

 7071 Oakwood Drive, Niagara Falls, ON, L2G 0J3

LIQUISTONE ®

INTENDED USE

100 % acrylic textured coating specifically designed for interior and exterior, above grade, masonry, concrete, and metal surfaces requiring a high performance textured finish.

PRODUCT DESCRIPTION

Liquistone ® is an acrylic coating for any vertical application that has alkali and efflorescence resistance. This coating provides resistance against water, UV light, staining and is breathable. **Liquistone** ® textured coatings provide a stain resistant texture that is excellent for high traffic, large wall areas. These finishes are a decorative textured coating ideal for high-rise apartments and condominiums, hospitals, schools, hotels, resorts and residential homes.

FEATURES

- 3 Textured finishes
- Resists wind driven rain
- Alkali resistant
- High build coating
- Freeze/thaw resistant
- UV resistant
- VOC compliant
- Excellent application Properties
- Excellent adhesion
- Self-priming
- Mildew Resistance

BENIFITS

- Decorative appearance
- Minimizes surface imperfections
- Customizable
- Any colour available
- Breathability
- Provides extra protection in fewer coats
- Improved quality and consistency
- More forgiving on substrates
- Quick application
- Looks newer Longer
- Blocks white crusty salt deposits
- Can be applied to fresh concrete at 7 days and/or surface less than 13 PH.

SURFACE PREPARATION

All surfaces to be coated must be clean, dry and free of contaminants. New concrete must be cured for a minimum of 7 days with no more than 18% moisture content. Any curing or hardening compounds, form oils, release agents or laitance must be removed by means of mechanical abrasion.

LIMITATIONS

- Apply when air, surface and product temperatures are above 50 ° F (10 °C) and surface temperature is at least 5°F (3 °C) above the dew point.
- Avoid exterior application late in day when dew and condensation are likely to form or if rain is anticipated. PROTECT FROM FREEZING. Do not use on steps, walkways, or other foot or vehicle traffic areas.
- Not recommended for immersion service.
- USE WITH ADEQUATE VENTILATION . KEEP OUT OF REACH OF CHILDREN.


RECOMMENDED SUBSTRATES



BRICK



CONCRETE



PLASTER



METAL



STUCCO



STONE



MASONRY

TECHNICAL DATA

Product Type:	100% acrylic	Weights Solid:	75% +/-2%
Packaging:	1 gal + 5 gal	Theoretical Coverage:	1604 sqft/US Gal. @ 1 mil WFT
Shelf - Life:	1 year in unopened container @ minimum 20 °C (68 °F)	Recommended DFT:	10 to 12 mils (min. two coats)
Colour:	Full Range	Cure time (@22°C):	Re-coat 12-16 hrs To handle - 24 hrs Full cure: 15-30 days
Sheen:	Flat 0-5 degrees	Fire resistance of dry film:	Self Extinguishing
Volume solids:	59% +/-2%	Cleanup:	Water and soap